



Reference photo

TECHNICAL DATA/ IQ color 160 gsm

GRAMMAGE		gsm	ISO 536	160	± 6
CALIPER		mm/1000	ISO 534	214	± 6
STIFFNESS L&W	MD CD	mN	ISO 2493		
ROUGHNESS BENDTSEN		ml/min	ISO 8791-2	210	± 50
POROCITY		ml/min	ISO 5636-3	650	± 350
MOISTURE		%	ISO 287	4.8	± 0.7
ABRASION		Mg	DIN 53 109	max 10	

PRODUCT MEETS Pr EN 12281
 TECHNICAL CUSTOMER SERVICE HOLDING

SIGNIFICANCE OF VALUES: 2 SIGMA
 01-12-2004